

**PRODUCT CODE:** XC-1108/03 Polyurethane Emulsion Adhesive  
**产品名称:** XC-1108/03 乳液型聚氨酯胶粘剂

A Polyurethane Emulsion adhesive XC-1108/03 has high adhesion to many substrates, excellent heat resistance and initial adhesion. It form a transparent flexible film after cured,.XC-1108/03 是一款乳液型聚氨酯胶粘剂它可以粘接许多材料,具有优良的耐热性和初粘力。在使用后可以形成透明柔软的薄膜。

### MAIN APPLICATIONS 主要应用

Adhesive especially designed in wet bonding adhesive applications with good open time. This product has excellent adhesion to PVC; bonding films and panel like PU, PS, ABS, fiberboard and PP,PE after pretreatment .It recommended to be mixed with Cross-linking Agent. This adhesive has strong bonding . 这个胶粘剂在合适的开放时间内粘接.它可以粘接 PVC,PU,PS, ABS, 纤维板以及经过预处理的 PP, PE 等材料.和固化剂配合使用, 是一款具有高粘接强度的产品。

Made thinking in friendly environment.  
环保理念

### PRODUCT SPECIFICATIONS 产品指标

Property	Specifications
Viscosity Brookfield, cp @ 25 °C 粘度	3500-6500
Solid content, % 固含量	47-52
Density, g/cc 比重	1.04 – 1.10
Cross-link Agent 固化剂	XC-1108B
*Mixing Ratio 混合比例	100:5 ~100:8
Full cured time 完全固化时间	48H
* Temperature resistance 耐热性能	Good (100 °C @400 g)
*Color 颜色	White Milky 乳白色

\* Typical value

### STORAGE CONDITIONS 储存条件

This product not contains volatile solvent. It doesn't flammable. Keep in dry place between 10 – 30 °C. It can't stock less than 5 °C . In this conditions the validate time is up to 8 months.

该产品不含挥发性溶剂, 不可燃, 干燥条件 10~30 °C, 保质期为 8 个月. 这个产品储存温度应高于 5 °C, 冬天运输时需要保温集装箱车。

Designed by:



José Ramón Cerezo  
Technical Director GSA

Approved by:



Cai Ping Chen  
Technical and R&D Manager  
GYMCOL China